



### PROJECT NAME

Park Ridge 6th Plat

### SPECIFICATIONS

Standard Proctor  
 ASTM D 698 Method A  
 Percent of Compaction N/A  
 Moisture Range  $\pm\%$  N/A

### PROCTOR TEST RESULTS

Max. Dry Density	Optimum Water Content
98.0 pcf	23.5%

### ATTERBERG LIMITS (ASTM D-4318)

Liquid Limit	Plastic Limit	Plasticity Index
63	21	42

### DESCRIPTION

Red-brown FAT CLAY

### SAMPLE LOCATION

Stockpile at Lot 308



### MOISTURE - DENSITY CURVE

Job No.	J030124.09	Test Date	4/2/2017
Sampled By	RFJ	Tested By	DDW
Sample Date	3/28/2018	Calc. By	ADC
Proctor No.	6818	Ch'd By	SCD