



PROJECT NAME

Park Ridge 6th Plat

SPECIFICATIONS

Standard Proctor
 ASTM D 698 Method A
 Percent of Compaction N/A
 Moisture Range \pm % N/A

PROCTOR TEST RESULTS

Max. Dry Density	Optimum Water Content
96.8 pcf	23.5%

ATTERBERG LIMITS (ASTM D-4318)

Liquid Limit	Plastic Limit	Plasticity Index

DESCRIPTION

Red-brown FAT CLAY treated with 5% Portland Cement
 Untreated Atterberg Limit LL 63 PL 21 PI 42

SAMPLE LOCATION

Stockpile at Lot 308



MOISTURE - DENSITY CURVE

Job No.	J030124.09	Test Date	4/3/2017
Sampled By	RFJ	Tested By	DDW
Sample Date	3/28/2018	Calc. By	ADC
Proctor No.	6819	Ch'd By	SCD