

Olathe
 1700 East 123rd Street
 Olathe, KS 66061
 Phone: 913-829-0078
 Fax: 913-829-0258

Client:
 Hunt Midwest
 8300 NE Underground Dr STE 100
 Kansas City, MO 64161-9736


Project:
 020-3102
 Hunt Midwest Hook Farms First Plat
 Lee's Summit, MO

Sample Information

Sample Number: 85634	Location: Existing Subgrade
Sampled By: McClure, Rigby	Location Details: Roadway - SW 26th Terrace
Sample Date: 03/22/2021	
Tested By: Kowal, David	
Tested Date: 03/24/2021	
Description: CL-CH Lean to Fat Clay - dark brown	

Laboratory Data

Lab Address: 1700 East 123rd Street, Olathe, KS, 66061



Maximum Dry Density (pcf):	102.8
Optimum Moisture (%):	19.1
Method:	A (ASTM D698)
Preparation Method:	Moist
Rammer Type:	Mechanical Round
Specific Gravity:	2.70
Specific Gravity Source:	Assumed

Remarks: [5% Portland Cement]