



Professional Service Industries, Inc.
2828 South 44th Street
Kansas City, KS 66106

Phone: (913) 310-1600
Fax: (913) 310-1601

Report No: CTR:03533627-47-C1

Issue No: 1

These test results apply only to the specific locations and materials noted and may not represent any other locations or elevations. This report may not be reproduced, except in full, without written permission by Professional Service Industries, Inc. If a non-compliance appears on this report, to the extent that the reported non-compliance impacts the project, the resolution is outside the PSI scope of engagement.

Approved Signatory: William Odell (Senior Project Manager)
Date of Issue: 9/7/2022

Concrete Test Report

Client: CORE STATES GROUP
3039 PREMIERE PARKWAY, SUITE 700
DULUTH, GA 30097

CC: C FAIRBANKS
CHRIS DIAMOND
GREG HELLBUSCH
J SANCHEZ
JOSE SANCHEZ
L MCKINZY
S KESHETTY
SUNIL DUBEY

Project: CHASE BANK-LEE'S SUMMIT
LEE'S SUMMIT, MO

Mix Data

Supplier: Geiger Ready-Mix
Plant: Geiger Ready Mix
Mix Identification: KC4KBDM40Q
Specified Design Strength (psi): 4000 at age 28 days

Sample Details

Date Sampled: 08/31/22	Date Received: 09/01/22	Specification: Mix Design	
General Location: Dumpster			
Sample Location: West side of dumpster driveway			
Curing Method: One day Field/Laboratory Cure			
Field Sample No.:	Initial Cure Temp (°F) High:		
	Low:		
Contractor:			
Ticket no.: 863172	Truck No.: 356		
Sampled By: Doug Deering			
Weather: Clear			
	Slump (in):	ASTM C 143	6
	Slump w/ plasticizer (in):		N/A
	Air Temp (°F):		74
	Concrete Temp (°F):	ASTM C 1064	80
	Air Content (%):	ASTM C 231	6.8
	Unit Weight (pcf):	ASTM C 138	N/A
	Volume of Density Measure (ft³):		N/A
	Batch Size (yd³): 7.0	Time Batched:	09:58
	Yd³ Placed: 7.0	Time Sampled:	10:20
	Water Added (gal) Before: 0	Time Placed:	10:35
	After: 0	Time in Truck (mins):	37

Compressive Strength of Concrete Cylinders

ASTM C 39

Specimen ID	Date Tested	Age (Days)	Diameter (in)	Length (in)	Area (in²)	Type of Cap	Maximum Load (lbf)	Fracture Type / Remarks	Compressive Strength (psi)	Tested By
03533627-47-C11	09/07/22	7	4.01	7.68	12.63	U	38790	2	3070	Robert Anderson
03533627-47-C12	09/28/22	28				U				
03533627-47-C13	09/28/22	28				U				
03533627-47-C14	09/28/22	28				U				
03533627-47-C15		Hold				U				

Average 28 Day Compressive Strength (psi)

Required Strength (psi) 4000

Notes

1. Sampling to ASTM C 172
2. Specimen(s) prepared to ASTM C 31
3. Capping B=Bonded ASTM C 617, U=Unbonded ASTM C 1231, C = Combined, G = Ground

Remarks

Fracture Type: 2 = C39: Vert crack/ cone opposite end; C1314: Cone & Shear