



Professional Service Industries, Inc.
2828 South 44th Street
Kansas City, KS 66106

Phone: (913) 310-1600
Fax: (913) 310-1601

Report No: FC:03533627-58

Issue No: 1

Concrete Field Report

These test results apply only to the specific locations and materials noted and may not represent any other locations or elevations. This report may not be reproduced, except in full, without written permission by Professional Service Industries, Inc. If a non-compliance appears on this report, to the extent that the reported non-compliance impacts the project, the resolution is outside the PSI scope of engagement.

Approved Signatory: William Odell (Senior Project Manager)
Date of Issue: 9/14/2022

Client: CORE STATES GROUP
3039 PREMIERE PARKWAY, SUITE
700
DULUTH, GA 30097

CC: C FAIRBANKS
CHRIS DIAMOND
GREG HELLBUSCH
J SANCHAZ
JOSE SANCHEZ
L MCKINZY
S KESHETTY
SUNIL DUBEY

Project: CHASE BANK-LEE'S SUMMIT
LEE'S SUMMIT, MO

General Field Data

Technician: Tyler Jordan

Test Date: 9/13/2022

Weather: Clear

Test Results

Set No.	# Spec.	Ticket	Batch Time	Unload Time	Cubic Yards Placed	Slump (in)	Air Content (%)	Air Temp. (°F)	Concrete Temp. (°F)
03533627-58-C1	5	864304	10:20	11:05	5.0	4.00	6.0	77	81

Location & Remarks

General Location: Light pole bases

Set No.	Location	Remarks
03533627-58-C1		

Mix Data

Set No.	Supplier	Mix	Design Strength (psi)
03533627-58-C1	Geiger Ready-Mix		4000

Notes

1. Applicable ASTM standards unless otherwise indicated: Slump: C143; Air Content: C231; Temperature: C1064; Sampling: C172; Unit Weight: C138;
2. Specimen(s) prepared to ASTM C 31
Sampled from Revolving Drum Truck Mixer (ASTM C 172, 5.2.3)

Remarks