

Phone: 913.780.4605



Customer Signature X

CONDITION OF SALE: All accounts payable C.O.D. There will be a \$25.00 service charge on returned checks

25746		CUSTOMER JD Bishop Construction LLC				PROJECT # 015523		PROJECT 2023 PRICING			
PLANT	DATE	TIME	ORDER	TRUCK	DRIN	/ER	REQUE	STED TIME	PREVIOUS TRUCK		
372	11/22/23 9:23	/22/23 9:23 9:19		302	87	4	11/22	2/23 9:50			
ELIVERY A 05 MISSO	ADDRESS DURI 150/LSMO		5		3RD ST - WI .N - EAST TO			- SOUTH TO W. N # 5))	ARD RD - EAS		
SLUMP USAGE DESCRIPTION PAVING											
PO NUMBE		JOB NUMBER									
LOAI QUANT		ORDERED QUANTITY	PROD ID	PRO	DUCT DESCRIF	PTION	UNIT	\$/UNIT	EXTENDED		
10.00 10.00 10.00 1.00 10.00	0 10.00 0	75.00 1.00 0.00 0.00 0.00	340D7E04 FIBERS-TS: 901.ENVN 901.FSCR NONTAXDE	3 3 LB (CY) TU ENVIRONME FUEL FEE P	IF-STRAND FIB ENTAL FEE - NO	ON TAX	yd lb /l ea /y				
		Will be		HEATED WATE	R						
TICKET NUMBER 37226167		GALLONS TO GALLONS TO		YARDS	YARDS X YARDS X		Sub-Total Sales Tax Total \$	7. 1			
	37226167		The second secon								
LEAVE PL	37226167	START POUR	G. FINISH POUR	ALLONS TO LEAVE JOB	YARDS ARRIVE PLANT		STING	Balance Due			

WARNING: INJURIES TO EYES, CAUSES SKIN IRRITATION READ THIS WARNING BEFORE USING. Contains Portland Cement.

Contact with wet (unhardened) concrete, mortar, cement, or cement mixture can cause skin irritation, sever chemical burns, or serious eye damage. Avoid contact with eyes and skin. Wear waterproof glowes, a fully buttoned long-sleeved shirt, full length trousers, and fight fitting eye protection when working with these materials. If you have to stand in wet concrete, use waterproof boots that are fight at tops and high enough to keep concrete from flowing into them. If you are finishing concrete, wear knee pads to protect knees. Wash wet concrete, mortar, cement or cement mixtures from your skin with fresh, clean water immediately after contact. Indirect contact through clothing can be as serious as direct contact, so promptly rinse out wet concrete, mortar, cement or cement mixtures from clothing. Seek immediate medical attention if you have persistent or severe discomfort. In case of eye contact, flush with plenty of water for at least 15 minutes. Consult a physician immediately.

KEEP OUT OF REACH OF CHILDREN

USER AGREES TO CONVEY THIS WARNING TO ALL PERSONS WHO MAY PURCHASE, USE OR COME IN CONTACT WITH WET (UNHARDENED) CONCRETE, MORTAR, CEMENT OR CEMENT MIXTURES, Concrete contains crystalline silica in concentrations greater than 0.1%. Respirable silica is considered by IARC and NTP to be a human carcinogen. Crystalline silica in wet concrete is not respirable and does not pose a hazard when the concrete is in its unhardened state. However, respirable dus can be generated by grinding, sawing, drilling, breaking, etc. hardened concrete. Wear and appropriate NIOSH approved respirator during these activities.

can be generated to	y grinding, sawing, driii	ng, browning, co		O/ Mar	% Moisture	Actual Wat	Trim
Material HOL-T1L(8) HOLSLAG 3/4GRANITE SAND-9 H2OGL AEA-92S	Design Qty 450 lb 150.0 lb 1701 lb 1266 lb 30.50 gl .60 /C 5.0 /C	Required 4500 lb 1500.0 lb 17095 lb 13231 lb 220.92 gl 36.00 oz 300.0 oz	Batched 4480 lb 1490.0 lb 17020 lb 13300 lb > 221.00 gl 36.00 oz 300.0 oz	% Var -0.44% -0.67% -0.44% 0.52% 0.04% 0.00% 0.00%	% Moisture 0.50% M 4.51% A	10 gl 69 gl 221.00 gl	50 gl
P_6420	5.0 /0	000.0					

Actual Load Slump:

38155 lb 5.00 in

Design W/C: Water in Truck:

Num Batches: Water/Cement: 0.424 0.0 gl

0.419 Adjust Water:

Design 0.0 gl / Load

305.0 gl

299.9 gl Actual

5.1 gl

To Add:

-0.5 gl / Trim Water: CYL