

Compressive Strength of Concrete

Test Method: ASTM C 39

Report Date: 06/24/2024

Sample: 446771

Alpha Omega Geotech, Inc

1701 State Avenue
Kansas City, KS 66102
Phone: 913-371-0000

Client:

Tailor Made Exteriors
1610 SE Hamblen Rd
Lee's Summit, MO 64081

Project:

230445
TM Fieldhouse
1600 SE Hamblen Rd
Lees Summit, MO 64081

Sample Details

Set #:	11	Technician:	Jeff Marquez	Batched:	09:42 CDT
Specimen Size:	4" X 8"	Cast By:	Jeff Marquez	Sampled:	10:06 CDT
Specimens In Set:	5	Date Cast:	06/12/24	Cast:	10:07 CDT
Truck / Ticket #:	477 / 93766	Sampled From:	Chute	Truck Empty:	10:15 CDT
Contractor:	Secon	Placement Method:	Chute	Placement Time:	33 (min)

Location

Placement Location:	Building Interior - Footing
Location Details:	Grade beam @ C/11-16 & 17/B-C
Sample Location / Notes:	C/11

Batch Log

Supplier:	Geiger
On-Site Admixtures:	None

Specifications

Strength:	4000 (psi)
-----------	------------

Field Measurements

Weather:	Sunny	Slump (in):	5 (ASTM C143)	Plastic Unit Weight:	
Air Temperature (F):	81	Concrete Temp (F):	78 (ASTM C1064)	Air Content:	
				Load Volume:	10.00 (yd ³)

Lab Test Results

Testing Lab: Alpha Omega Geotech, 1701 State Ave, Kansas City, KS, 66102

Specimen Number	Test Age Days	Test Date	Field / Lab Cure Days	Average Cylinder Diameter (in)	Cylinder Area (in ²)	Max Load (lbs)	Strength (psi)	Fracture Type	Break Remark	Capping Method
11-1	7	06/19/24	1 / 6	4.00	12.57	44,810	3,570	3		N
11-2	28	07/10/24	1 / 27							
11-3	28	07/10/24	1 / 27							
11-4	28	07/10/24	1 / 27							
11-5	56 H	08/07/24	1 / 55							

Test Age Average Strengths (psi): 7 Day - 3570

Capping Methods

Tested By: Marquis Gaston (1)

N: Neoprene

Checked In : 06/13/2024 (1,2,3,4,5)



TYPE 1 TYPE 2 TYPE 3 TYPE 4 TYPE 5 TYPE 6