

# Compressive Strength of Concrete

Test Method: ASTM C 39

Report Date: 07/29/2024

Sample: 447114

## Alpha Omega Geotech, Inc

1701 State Avenue  
Kansas City, KS 66102  
Phone: 913-371-0000

## Client:

Tailor Made Exteriors  
1610 SE Hamblen Rd  
Lee's Summit, MO 64081

## Project:

230445  
TM Fieldhouse  
1600 SE Hamblen Rd  
Lees Summit, MO 64081

## Sample Details

Set #:	16	Technician:	Chase Behler	Batched:	03:37 CDT
Specimen Size:	4" X 8"	Cast By:	Chase Behler	Sampled:	04:00 CDT
Specimens In Set:	5	Date Cast:	07/18/24	Cast:	04:15 CDT
Truck / Ticket #:	453 / 1006516	Sampled From:	Chute	Truck Empty:	04:18 CDT
Contractor:	Secon Construction	Placement Method:	Pump	Placement Time:	41 (min)

## Location

Placement Location: Building Interior - Slab on Grade  
Location Details: Floor slab pour  
Sample Location / Notes: NW corner of slab

## Batch Log

Supplier:	Geiger	Mix Design:	P4UC540V445	Strength:	4000 (psi)
Plant:	Lee's Summit				
On-Site Admixtures:	None				

## Specifications

## Field Measurements

Weather:	Clear	Slump (in):	5 (ASTM C143)	Plastic Unit Weight:	
Air Temperature (F):	64	Concrete Temp (F):	78 (ASTM C1064)	Air Content:	
				Load Volume:	10.00 (yd³)

## Lab Test Results

Testing Lab: Alpha Omega Geotech, 1701 State Ave, Kansas City, KS, 66102

Specimen Number	Test Age Days	Test Date	Field / Lab Cure Days	Average Cylinder Diameter (in)	Cylinder Area (in²)	Max Load (lbs)	Strength (psi)	Fracture Type	Break Remark	Capping Method
16-1	7	07/25/24	2 / 5	4.00	12.57	57,440	4,570	3		N
16-2	28	08/15/24	2 / 26							
16-3	28	08/15/24	2 / 26							
16-4	28	08/15/24	2 / 26							
16-5	56 H	09/12/24	2 / 54							

Test Age Average Strengths (psi): 7 Day - 4570

## Capping Methods

Tested By: Marquis Gaston (1)	N: Neoprene
Checked In : 07/20/2024 (1,2,3,4,5)	

